

TECHNICAL DATA SHEET of WHOLE TYRE RECLAIM RUBBER

GRADE: SNR-112(MEDIUM)

CHEMICAL PROPERTIES

TECHNICAL DATA SPECIFICATION	TEST METHOD	SNR-112(MEDIUM)
ACETONE EXTRACT (%)	ASTM D 297-18	14 \pm 4
ASH CONTENT (%)	ASTM D 297-18	10 Max
CARBON BLACK (%)	ASTM E1131	25 \pm 2
VOLATILE MATTER (%)		1.0(Max)
RHC (%)	ASTM E1131	50(Min)

PHYSICAL PROPERTIES

SPECIFIC GRAVITY (gm/cc)	ASTM D 297-18	1.14 \pm 0.03
TENSILE STRENGTH(Kg/cm ²)	ASTM D 412	45(Min)
ELONGATION (%)	ASTM D 412	210 Min
HARDNESS AT SHORE "A"	ASTM D 2240	57 \pm 5
MOONEY VISCOSITY(1+4@100°C)	ASTM D 1646	25-55

SNR Reclamations Pvt. Ltd.

114, Green Field, Near Pakhowal Road, Ludhiana - 141001 (Pb.) - INDIA.
Telephone: +91-161-4645114 **Mobile:** +91-9876066777, 750888368
Email : jas.snorreclamations@gmail.com, snorreclamations@gmail.com
Website : www.snorreclamations.com